



Declaration of Performance
(according to regulation EU No 305/2011)

No. AMHU-2/01-CPR-13-1

- 1) Code of the product type: **1.0038**
2) Type: **Sections/Bars S235JR according EN 10025-2**

Intended use or uses of the construction product, in accordance with the applicable harmonised technical specification, as foreseen by the manufacturer:

To be used in welded, bolted and riveted structures

- 3) ArcelorMittal Hunedoara SA
DJ 687, no. 4
Cod 331111, Hunedoara – Romania
Tel 004-0254712785
Fax 004-0254715311
www.arcelormittal.com/sections

System of assessment and verification of constancy of performance of the product:
System 2+

Notified factory production control certification body No. 1823
QUALITAS performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment, and evaluation of factory production control and issued the certificate of conformity of the factory production control.

The performance of the product identified in points 1 and 2 is in conformity with the declared performance in the table.

This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 3. Signed for and on behalf of the manufacturer by:

Kumar Amit
CEO

Cristea Ileana
Quality Manager

Date : 01.07.2013

Essential characteristic		Performance		Harmonised technical specification	
Tolerances on dimensions and shape	Angles		EN10056-2		EN 10025-1:2004
	I and H sections		EN 10034		
	Tapered Flange I		EN 10024		
	UPE, UPN		EN 10279		
	Flat / Square / Round / T bars		EN 10058/EN 10059/EN 10060/EN 10055		
Yield strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min		
		16	235		
	16	40	225		
	40	63	215		
	63	80			
	80	100			
	100	140	195		
Tensile strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min	max	
	≤3	100	360	510	
	100	140	350	500	
Elongation	Nominal thickness (mm)		Values (%)		
	>	≤	min		
	≤3	40	26		
	40	63	25		
	63	100	24		
100	140	22			
Impact strength	Nominal thickness (mm)		Values (J)		
	>	≤	min		
		140	27 at +20°C		
Weldability	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		30	0,35		
	30	40	0,35		
40	140	0,38			
Durability (Chemical composition)	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		140	C* : 0,17 Mn : 1,40 P : 0,040	Cu : 0,55 S : 0,040 N** : 0,012	
* For nominal thickness > 40 mm C: 0,20. For nominal thickness >100 mm: C content upon agreement					
** The max. value for nitrogen does not apply if the chemical composition shows a minimum total Al content of 0,020% or if sufficient other N binding elements are present					



Declaration of Performance
(according to regulation EU No 305/2011)

No. AMHU-2/02-CPR-13-1

- 1) Code of the product type: **1.0114**
2) Type: **Sections/Bars S235J0 according EN 10025-2**

Intended use or uses of the construction product, in accordance with the applicable harmonised technical specification, as foreseen by the manufacturer:

To be used in welded, bolted and riveted structures

- 3) ArcelorMittal Hunedoara SA
DJ 687, no. 4
Cod 331111, Hunedoara – Romania
Tel 004-0254712785
Fax 004-0254715311
www.arcelormittal.com/sections

System of assessment and verification of constancy of performance of the product:
System 2+

Notified factory production control certification body No. 1823
QUALITAS performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment, and evaluation of factory production control and issued the certificate of conformity of the factory production control.

The performance of the product identified in points 1 and 2 is in conformity with the declared performance in the table.

This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 3. Signed for and on behalf of the manufacturer by:

Kumar Amit
CEO

Cristea Ileana
Quality Manager

Date : 01.07.2013

Essential characteristic		Performance		Harmonised technical specification	
Tolerances on dimensions and shape	Angles		EN10056-2		EN 10025-1:2004
	I and H sections		EN 10034		
	Tapered Flange I		EN 10024		
	UPE, UPN		EN 10279		
	Flat / Square / Round / T bars		EN 10058/EN 10059/EN 10060/EN 10055		
Yield strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min		
		16	235		
	16	40	225		
	40	63	215		
	63	80			
	80	100			
	100	140	195		
Tensile strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min	max	
	≤3	100	360	510	
	100	140	350	500	
Elongation	Nominal thickness (mm)		Values (%)		
	>	≤	min		
	≤3	40	26		
	40	63	25		
	63	100	24		
100	140	22			
Impact strength	Nominal thickness (mm)		Values (J)		
	>	≤	min		
		140	27 at 0°C		
Weldability	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		30	0,35		
	30	40	0,35		
40	140	0,38			
Durability (Chemical composition)	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		140	C* : 0,17 Mn : 1,40 P : 0,035	Cu : 0,55 S : 0,035 N** : 0,012	
* For nominal thickness >100 mm: C content upon agreement.					
** The max. value for nitrogen does not apply if the chemical composition shows a minimum total Al content of 0,020% or if sufficient other N binding elements are present					



Declaration of Performance
(according to regulation EU No 305/2011)

No. AMHU-2/03-CPR-13-1

- 1) Code of the product type: **1.0117**
 2) Type: **Sections/Bars S235J2 according EN 10025-2**

Intended use or uses of the construction product, in accordance with the applicable harmonised technical specification, as foreseen by the manufacturer:

To be used in welded, bolted and riveted structures

- 3) ArcelorMittal Hunedoara SA
 DJ 687, no. 4
 Cod 331111, Hunedoara – Romania
 Tel 004-0254712785
 Fax 004-0254715311
 www.arcelormittal.com/sections

System of assessment and verification of constancy of performance of the product:
 System 2+

Notified factory production control certification body No. 1823
 QUALITAS performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment, and evaluation of factory production control and issued the certificate of conformity of the factory production control.

The performance of the product identified in points 1 and 2 is in conformity with the declared performance in the table.

This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 3. Signed for and on behalf of the manufacturer by:

Kumar Amit
 CEO

Cristea Ileana
 Quality Manager

Date : 01.07.2013

Essential characteristic		Performance		Harmonised technical specification	
Tolerances on dimensions and shape	Angles		EN10056-2		EN 10025-1:2004
	I and H sections		EN 10034		
	Tapered Flange I		EN 10024		
	UPE, UPN		EN 10279		
	Flat / Square / Round / T bars		EN 10058/EN 10059/EN 10060/EN 10055		
Yield strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min		
		16	235		
	16	40	225		
	40	63	215		
	63	80			
	80	100			
	100	140	195		
Tensile strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min	max	
	≤3	100	360	510	
	100	140	350	500	
Elongation	Nominal thickness (mm)		Values (%)		
	>	≤	min		
	≤3	40	26		
	40	63	25		
	63	100	24		
100	140	22			
Impact strength	Nominal thickness (mm)		Values (J)		
	>	≤	min		
		140	27 at -20°C		
Weldability	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		30	0,35		
	30	40	0,35		
40	140	0,38			
Durability (Chemical composition)	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		140	C* : 0,17 Mn : 1,40 P : 0,030	Cu : 0,55 S : 0,030	
* For nominal thickness >100 mm: C content upon agreement. Fully killed steel containing nitrogen binding element in amounts sufficient to bind the available nitrogen (for example min. 0,02% Al)					



Declaration of Performance
(according to regulation EU No 305/2011)

No. AMHU-2/04-CPR-13-1

- 1) Code of the product type: **1.0044**
2) Type: **Sections/Bars S275JR according EN 10025-2**

Intended use or uses of the construction product, in accordance with the applicable harmonised technical specification, as foreseen by the manufacturer:

To be used in welded, bolted and riveted structures

- 3) ArcelorMittal Hunedoara SA
DJ 687, no. 4
Cod 331111, Hunedoara – Romania
Tel 004-0254712785
Fax 004-0254715311
www.arcelormittal.com/sections

System of assessment and verification of constancy of performance of the product:
System 2+

Notified factory production control certification body No. 1823
QUALITAS performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment, and evaluation of factory production control and issued the certificate of conformity of the factory production control.

The performance of the product identified in points 1 and 2 is in conformity with the declared performance in the table.

This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 3. Signed for and on behalf of the manufacturer by:

Kumar Amit
CEO

Cristea Ileana
Quality Manager

Date : 01.07.2013

Essential characteristic		Performance		Harmonised technical specification	
Tolerances on dimensions and shape	Angles		EN10056-2		EN 10025-1:2004
	I and H sections		EN 10034		
	Tapered Flange I		EN 10024		
	UPE, UPN		EN 10279		
	Flat / Square / Round / T bars		EN 10058/EN 10059/EN 10060/EN 10055		
Yield strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min		
		16	275		
	16	40	265		
	40	63	255		
	63	80	245		
	80	100	235		
	100	140	225		
Tensile strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min	max	
	≤3	100	410	560	
	100	140	400	540	
Elongation	Nominal thickness (mm)		Values (%)		
	>	≤	min		
	≤3	40	23		
	40	63	22		
	63	100	21		
100	140	19			
Impact strength	Nominal thickness (mm)		Values (J)		
	>	≤	min		
		140	27 at +20°C		
Weldability	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		30	0,40		
	30	40	0,40		
40	140	0,42			
Durability (Chemical composition)	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		140	C* : 0,21 Mn : 1,50 P : 0,040	Cu : 0,55 S : 0,040 N** : 0,012	
	* For nominal thickness > 40 mm C: 0,22. For nominal thickness >100 mm: C content upon agreement ** The max. value for nitrogen does not apply if the chemical composition shows a minimum total Al content of 0,020% or if sufficient other N binding elements are present				



Declaration of Performance
(according to regulation EU No 305/2011)

No. AMHU-2/05-CPR-13-1

- 1) Code of the product type: **1.0143**
 2) Type: **Sections/Bars S275J0 according EN 10025-2**

Intended use or uses of the construction product, in accordance with the applicable harmonised technical specification, as foreseen by the manufacturer:

To be used in welded, bolted and riveted structures

- 3) ArcelorMittal Hunedoara SA
 DJ 687, no. 4
 Cod 331111, Hunedoara – Romania
 Tel 004-0254712785
 Fax 004-0254715311
 www.arcelormittal.com/sections

System of assessment and verification of constancy of performance of the product:
 System 2+

Notified factory production control certification body No. 1823
 QUALITAS performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment, and evaluation of factory production control and issued the certificate of conformity of the factory production control.

The performance of the product identified in points 1 and 2 is in conformity with the declared performance in the table.

This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 3. Signed for and on behalf of the manufacturer by:

Kumar Amit
 CEO

Cristea Ileana
 Quality Manager

Date : 01.07.2013

Essential characteristic		Performance		Harmonised technical specification	
Tolerances on dimensions and shape	Angles		EN10056-2		EN 10025-1:2004
	I and H sections		EN 10034		
	Tapered Flange I		EN 10024		
	UPE, UPN		EN 10279		
	Flat / Square / Round / T bars		EN 10058/EN 10059/EN 10060/EN 10055		
Yield strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min		
		16	275		
	16	40	265		
	40	63	255		
	63	80	245		
	80	100	235		
	100	140	225		
Tensile strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min	max	
	≤3	100	410	560	
	100	140	400	540	
Elongation	Nominal thickness (mm)		Values (%)		
	>	≤	min		
	≤3	40	23		
	40	63	22		
	63	100	21		
100	140	19			
Impact strength	Nominal thickness (mm)		Values (J)		
	>	≤	min		
		140	27 at 0°C		
Weldability	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		30	0,40		
	30	40	0,40		
40	140	0,42			
Durability (Chemical composition)	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		140	C* : 0,18 Mn : 1,50 P : 0,035	Cu : 0,55 S : 0,035 N** : 0,012	
* For nominal thickness >100 mm: C content upon agreement.					
** The max. value for nitrogen does not apply if the chemical composition shows a minimum total Al content of 0,020% or if sufficient other N binding elements are present					



Declaration of Performance
(according to regulation EU No 305/2011)

No. AMHU-2/06-CPR-13-1

- 1) Code of the product type: **1.0145**
2) Type: **Sections/Bars S275J2 according EN 10025-2**

Intended use or uses of the construction product, in accordance with the applicable harmonised technical specification, as foreseen by the manufacturer:

To be used in welded, bolted and riveted structures

- 3) ArcelorMittal Hunedoara SA
DJ 687, no. 4
Cod 331111, Hunedoara – Romania
Tel 004-0254712785
Fax 004-0254715311
www.arcelormittal.com/sections

System of assessment and verification of constancy of performance of the product:
System 2+

Notified factory production control certification body No. 1823
QUALITAS performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment, and evaluation of factory production control and issued the certificate of conformity of the factory production control.

The performance of the product identified in points 1 and 2 is in conformity with the declared performance in the table.

This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 3. Signed for and on behalf of the manufacturer by:

Kumar Amit
CEO

Cristea Ileana
Quality Manager

Date : 01.07.2013

Essential characteristic		Performance		Harmonised technical specification
Tolerances on dimensions and shape	Angles		EN10056-2	
	I and H sections		EN 10034	
	Tapered Flange I		EN 10024	
	UPE, UPN		EN 10279	
	Flat / Square / Round / T bars		EN 10058/EN 10059/EN 10060/EN 10055	
Yield strength	Nominal thickness (mm)		Values (MPa)	
	>	≤	min	
		16	275	
	16	40	265	
	40	63	255	
	63	80	245	
	80	100	235	
	100	140	225	
Tensile strength	Nominal thickness (mm)		Values (MPa)	
	>	≤	min	max
	≤3	100	410	560
	100	140	400	540
Elongation	Nominal thickness (mm)		Values (%)	
	>	≤	min	
	≤3	40	23	
	40	63	22	
	63	100	21	
100	140	19		
Impact strength	Nominal thickness (mm)		Values (J)	
	>	≤	min	
		140	27 at -20°C	
Weldability	Nominal thickness (mm)		Values (%)	
	>	≤	max	
		30	0,40	
	30	40	0,40	
40	140	0,42		
Durability (Chemical composition)	Nominal thickness (mm)		Values (%)	
	>	≤	max	
		140	C* : 0,18 Mn : 1,50 P : 0,030	Cu : 0,55 S : 0,030
* For nominal thickness >100 mm: C content upon agreement. Fully killed steel containing nitrogen binding element in amounts sufficient to bind the available nitrogen (for example min. 0,02% Al)				

EN 10025-1:2004



Declaration of Performance
(according to regulation EU No 305/2011)

No. AMHU-2/07-CPR-13-1

- 1) Code of the product type: **1.0045**
- 2) Type: **Sections/Bars S355JR according EN 10025-2**

Intended use or uses of the construction product, in accordance with the applicable harmonised technical specification, as foreseen by the manufacturer:

To be used in welded, bolted and riveted structures

- 3) ArcelorMittal Hunedoara SA
DJ 687, no. 4
Cod 331111, Hunedoara – Romania
Tel 004-0254712785
Fax 004-0254715311
www.arcelormittal.com/sections

System of assessment and verification of constancy of performance of the product:
System 2+

Notified factory production control certification body No. 1823

QUALITAS performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment, and evaluation of factory production control and issued the certificate of conformity of the factory production control.

The performance of the product identified in points 1 and 2 is in conformity with the declared performance in the table.

This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 3. Signed for and on behalf of the manufacturer by:

Kumar Amit
CEO

Cristea Ileana
Quality Manager

Date : 01.07.2013

Essential characteristic		Performance		Harmonised technical specification	
Tolerances on dimensions and shape	Angles		EN10056-2		EN 10025-1:2004
	I and H sections		EN 10034		
	Tapered Flange I		EN 10024		
	UPE, UPN		EN 10279		
	Flat / Square / Round / T bars		EN 10058/EN 10059/EN 10060/EN 10055		
Yield strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min		
		16	355		
	16	40	345		
	40	63	335		
	63	80	325		
	80	100	315		
	100	140	295		
Tensile strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min	max	
	≤3	100	470	630	
	100	140	450	600	
Elongation	Nominal thickness (mm)		Values (%)		
	>	≤	min		
	≤3	40	22		
	40	63	21		
	63	100	20		
100	140	18			
Impact strength	Nominal thickness (mm)		Values (J)		
	>	≤	min		
		140	27 at +20°C		
Weldability	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		30	0,45		
	30	40	0,47		
40	140	0,47			
Durability (Chemical composition)	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		140	C* : 0,24 Si : 0,55 Mn : 1,60 P : 0,040	Cu : 0,55 S : 0,040 N** : 0,012	
* For nominal thickness >100 mm: C content upon agreement.					
** The max. value for nitrogen does not apply if the chemical composition shows a minimum total Al content of 0,020% or if sufficient other N binding elements are present					



Declaration of Performance
(according to regulation EU No 305/2011)

No. AMHU-2/08-CPR-13-1

- 1) Code of the product type: **1.0553**
- 2) Type: **Sections/Bars S355J0 according EN 10025-2**

Intended use or uses of the construction product, in accordance with the applicable harmonised technical specification, as foreseen by the manufacturer:

To be used in welded, bolted and riveted structures

- 3) ArcelorMittal Hunedoara SA
DJ 687, no. 4
Cod 331111, Hunedoara – Romania
Tel 004-0254712785
Fax 004-0254715311
www.arcelormittal.com/sections

System of assessment and verification of constancy of performance of the product:
System 2+

Notified factory production control certification body No. 1823

QUALITAS performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment, and evaluation of factory production control and issued the certificate of conformity of the factory production control.

The performance of the product identified in points 1 and 2 is in conformity with the declared performance in the table.

This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 3. Signed for and on behalf of the manufacturer by:

Kumar Amit
CEO

Cristea Ileana
Quality Manager

Date : 01.07.2013

Essential characteristic		Performance		Harmonised technical specification	
Tolerances on dimensions and shape	Angles		EN10056-2		EN 10025-1:2004
	I and H sections		EN 10034		
	Tapered Flange I		EN 10024		
	UPE, UPN		EN 10279		
	Flat / Square / Round / T bars		EN 10058/EN 10059/EN 10060/EN 10055		
Yield strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min		
		16	355		
	16	40	345		
	40	63	335		
	63	80	325		
	80	100	315		
	100	140	295		
Tensile strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min	max	
	≤3	100	470	630	
	100	140	450	600	
Elongation	Nominal thickness (mm)		Values (%)		
	>	≤	min		
	≤3	40	22		
	40	63	21		
	63	100	20		
100	140	18			
Impact strength	Nominal thickness (mm)		Values (J)		
	>	≤	min		
		140	27 at 0°C		
Weldability	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		30	0,45		
	30	40	0,47		
40	140	0,47			
Durability (Chemical composition)	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		140	C* : 0,20 Si : 0,55 Mn : 1,60 P : 0,035	Cu : 0,55 S : 0,035 N** : 0,012	
* For nominal thickness > 30 mm C: 0,22. For nominal thickness >100 mm: C content upon agreement					
** The max. value for nitrogen does not apply if the chemical composition shows a minimum total Al content of 0,020% or if sufficient other N binding elements are present					



Declaration of Performance
(according to regulation EU No 305/2011)

No. AMHU-2/09-CPR-13-1

- 1) Code of the product type: **1.0577**
 2) Type: **Sections/Bars S355J2 according EN 10025-2**

Intended use or uses of the construction product, in accordance with the applicable harmonised technical specification, as foreseen by the manufacturer:

To be used in welded, bolted and riveted structures

- 3) ArcelorMittal Hunedoara SA
 DJ 687, no. 4
 Cod 331111, Hunedoara – Romania
 Tel 004-0254712785
 Fax 004-0254715311
 www.arcelormittal.com/sections

System of assessment and verification of constancy of performance of the product:
 System 2+

Notified factory production control certification body No. 1823
 QUALITAS performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment, and evaluation of factory production control and issued the certificate of conformity of the factory production control.

The performance of the product identified in points 1 and 2 is in conformity with the declared performance in the table.

This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 3. Signed for and on behalf of the manufacturer by:

Kumar Amit
 CEO

Cristea Ileana
 Quality Manager

Date : 01.07.2013

Essential characteristic		Performance		Harmonised technical specification	
Tolerances on dimensions and shape	Angles		EN10056-2		EN 10025-1:2004
	I and H sections		EN 10034		
	Tapered Flange I		EN 10024		
	UPE, UPN		EN 10279		
	Flat / Square / Round / T bars		EN 10058/EN 10059/EN 10060/EN 10055		
Yield strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min		
		16	355		
	16	40	345		
	40	63	335		
	63	80	325		
	80	100	315		
	100	140	295		
Tensile strength	Nominal thickness (mm)		Values (MPa)		
	>	≤	min	max	
	≤3	100	470	630	
	100	140	450	600	
Elongation	Nominal thickness (mm)		Values (%)		
	>	≤	min		
	≤3	40	22		
	40	63	21		
	63	100	20		
100	140	18			
Impact strength	Nominal thickness (mm)		Values (J)		
	>	≤	min		
		140	27 at -20°C		
Weldability	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		30	0,45		
	30	40	0,47		
40	140	0,47			
Durability (Chemical composition)	Nominal thickness (mm)		Values (%)		
	>	≤	max		
		140	C* : 0,20 Si : 0,55 Mn : 1,60	Cu : 0,55 S : 0,030 P : 0,030	
* For nominal thickness > 30 mm C: 0,22. For nominal thickness >100 mm: C content upon agreement Fully killed steel containing nitrogen binding element in amounts sufficient to bind the available nitrogen (for example min. 0,02% Al)					